

Technical Datasheet Castello Classic

CIF:RO18441743 Adresa: Calea 13 Septembrie nr 162, sector 5, Bucuresti

Adresa web: www.laminat-parchet.ro

Best Invest Group SRL

Tel.: 0722 458 121 / 0737 009 009 Email: magazinbestinvest@gmail.com

Made by Kronospan

Made by Kronospan

Direct Pressure Laminate

Direct Pressure Laminate, Level of use according to EN 13329: class 23/32 - AC4

Heavy domestic use	General comm	az ercial use	guarantee The guarantee applies according to warranty		ÉMISSIONS DANS L'AIR INTÉRIEUR
dimension	thickness (d)	s (d) 8 ± 0,50 mm · dmax - dmi			
	length	1285 ± 0,50 mm			
	width (b)	192 ± 0,10 mm · bmax - bmin		≤ 0,20 mm	EN 14041:2004/AC:2006; Cfl-s1; E1; D5; PCP<5ppm
profile	long side	twin clic	short side	twin clic	For internal use as floor coverings (see EN 14041); DOP SM01 14012016
TOLERANCE					
squareness		EN 13329		≤ 0,20 mm	
straightness		EN 13329		≤ 0,30 mm	
flatness crosswise		EN 13329		concave: ≤ 0,15% · convex: ≤ 0,20%	
flatness length		EN 13329		concave: ≤ 0,50% · convex: ≤ 1,00%	
gaps between elements		EN 13329		average: ≤ 0,15 mm · max: ≤ 0,20 mm	
height difference between elements		EN 13329		average: ≤ 0,10 mm · max: ≤ 0,15 mm	
misalignment				± 2 mm	
TEST					
abrasion resistance		EN 13329		AC4 (≥ 4000 rpm)	
impact resistance		EN 13329		small ball ≥ 12 N · big ball ≥750 mm	
stain resistance	group 1 & 2	EN 13329		grade 5	
	group 3			≥ grade 4	
castor chair test		EN 13329		no change in appearance or damage, as defined per EN 425	
effect of a furniture leg		EN 13329		no damage shall be visible, when testet with foot type 0	
thickness swelling		EN 13329		≤ 18%	
static indentation		EN 13329		≤ 0,05 mm	
light fastness		EN 13329		grey scale ≥ 4 at blue wool grade 6	
dimensional variations after changes in relative humidity		EN 13329		length	nwise ≤ 0,9 mm · crosswise ≤ 0,9 mm
locking strength		EN 13329		length ≥ 1 kN/m · width ≥ 2 kN/m	
surface soundness		EN 13329		≥ 1,25 N/mm²	
ENVIRONMENT					
emission of formaldeh	lyde	EN 717-1		Klasse E1	
PHYSICAL BEHAVIOR					
fire behavior		EN 13501-1		Cfl s1	
slide resistance thermal resistance		EN 13893		technical class DS	
thermal conductivity		EN 12667		0,108 (m ² K)/W ± 15% 0,126 W/(m*K) ± 15%	
antistatic behavior		EN 12664 EN 1815		0,126 W/(m²K) ± 15% body voltage ≤ 2kV	
*Detailed warranty and differences and the second state of the sec		CIOI VIZ		bouy voltage ≤ 2kV	

^{*}Detailed warranty conditions are available at www. krono-original.com

The data sheet is updated regularly to meet new technological standards. This version replaces all previous versions as well as those which are undated. This version takes effect upon creation. Version 01/2017